

## PolyZone Silver 20 Xtra

Film for Application to Rigid Plastic Glazing

### OPTICAL & SOLAR PROPERTIES

	Single Pane
Visible Light Transmitted	16 %
Visible Light Reflected (Int)	63 %
Visible Light Reflected (Ext)	64 %
Ultra Violet Block	99 %
Total Solar Energy Reflected	65 %
Total Solar Energy Transmitted	12 %
Total Solar Energy Absorbed	23 %
Emissivity (Room Side)	0.84
Glare Reduction	82 %
Shading Coefficient	0.22
Solar Heat Gain Coeff. (G-Value)	0.19
U-Value Winter (IP)	1.04
U-Value Winter (SI)	5.91
Luminous Efficacy	0.75
Total Solar Energy Rejected	81 %

R0705XP - PolyZone Silver 20 Xtra Pressure Sensitive Adhesive



Single pane  
Energy Savings



Ed-A DS No 1910 August 2011