

Silver 35 Xtra

OPTICAL & SOLAR PROPERTIES

	Single Pane	Double Pane
Visible Light Transmitted	33 %	31 %
Visible Light Reflected (Int)	42 %	44 %
Visible Light Reflected (Ext)	42 %	43 %
Ultra Violet Block	99 %	99 %
Total Solar Energy Reflected	45 %	46 %
Total Solar Energy Transmitted	25 %	22 %
Total Solar Energy Absorbed	30 %	32 %
Emissivity (Room Side)	0.84	0.84
Glare Reduction	63 %	62 %
Shading Coefficient	0.39	0.32
Solar Heat Gain Coeff. (G-Value)	0.34	0.28
U-Value Winter (IP)	1.04	0.48
U-Value Winter (SI)	5.91	2.73
Luminous Efficacy	0.84	0.96
Total Solar Energy Rejected	66 %	72 %

R07035X - Silver 35 Xtra Pressure Sensitive Adhesive

